





KABITENE

SELF-ADHESIVE BITUMINOUS MEMBRANE IN STRIPS

REINFORCEMENT
COMPOUND
FINISHING
APPLICATION METHOD
DESTINATION OF USE

KABITENE

FPC CODE

NON WOVEN POLYESTER FABRIC

BITUMEN – BI-COMPOUND KABITENE: POLYETHYLENE FILM

SELF-ADHESIVE

EN 13707 WATERPROOFING SYSTEM MULTILAYER: FINISHING LAYER - UNDER LAYER

GB14/92056



Self-adhesive bituminous membrane supplied in strips having a standard height of 5-10-15-20 cm and available in other sizes upon demand.

Fields of application

Suitable as an anti-corrosive coating for buried pipes and for all types of maintenance works such as eaves gutters,

downpipes, valley gutters, canopies, etc.

Stratigraphy

- 1. Polypropylene film
- 2. Compound SBS
- 3. Non woven polyester fabric reinforcement
- 4. Compound SBS
- $\textbf{5.} \ \mathsf{Finishing:} \ \mathsf{POLYETHYLENE} \ \mathsf{FILM}$













KABITENE

SELF-ADHESIVE BITUMINOUS MEMBRANE IN STRIPS

Technical Features

Parameter	KABITENE	Unit of measure	Tolerance	Regulations
VISIBLE DEFECTS	Exceeds	Visual	-	EN 1850-1
LENGTH	15	m	-1 %	EN 1848-1
WIDTH	1	m	-1 %	EN 1848-1
STRAINGHTNESS	Exceeds < 20mm/10m	-	-	EN 1848-1
MASS PER UNIT AREA	NPD	Kg/m ²	- 10 %	EN 1849-1
THICKNESS	2	mm	- 0,2	EN 1849-1
WATERTIGHTNESS	Exceeds > 60	kPa	-	EN 1928:2000
WATERTIGHTNESS AFTER STRETCHING	NPD	%	-	EN 13897
EXTERNAL FIRE PERFORMANCE	F ROOF	-	-	EN 13501-5
REACTION TO FIRE	F	Classe	-	EN 13501-1
TENSILE PROPERTIES MAXIMUM LOAD AT BREAK Longitudinal Transversal	400 300	N/50 mm	- 20 % - 20 %	EN 12311-1
ELONGATION AT BREAK Longitudinal Transversal	35 35	%	- 15 in ass. - 15 in ass.	EN 12311-1
RESISTANCE TO TEARING (nail method) Longitudinal Transversal	120 120	N	- 30 % - 30 %	EN 12310-1
RESISTANCE TO IMPACT	NPD	mm	≥	EN 12691
RESISTANCE TO STATING LOADING	NPD	Kg	≥	EN 12730-1
COLD FLEXIBILITY	-20	°C	≤	EN 1109
FLOW RESISTANCE AT ELEVATED TEMPERATURE	100	°C	≥	EN 1110
DIMENSIONAL STABILITY	0,3	%	≤	EN 1107-1
FORM STABILITY UNDER CYCLIC TEMPERAURE CHANGE	NPD	mm	-	EN 1108
ARTIFICIAL AGEING BEHAVIOUR (FLOW RESISTANCE)	NPD	∆T °C	-	EN 1296
ARTIFICIAL AGEING BEHAVIOUR (VISIBLE DEFECTS)	NPD	-	-	EN 1297
ADHESION OF GRANULES	NPD	%	- 5 in ass.	EN 12039
WATER VAPOUR PROPERTIES	NPD	μ	-	EN 1931
RESISTANCE TO ROOTS	NPD	-	-	EN 13948
PEEL RESISTANCE Steel Support	50	N/50 mm	-	EN 12316-1
PEEL RESISTANCE AFTER AGEING Steel Support	30	N/50 mm	-	EN 12317-1

Note: NPD = No Performance Declared according to the EU Directive on Construction Products

It is impossible to ensure uniformity of color of slated products, because the only slate manufacturer makes no warranty about. All self-protected products with slate chippings undergo color changes over time as a function of exposure to atmospheric agents. These color variations tend to conform gradually. AVAILABLE COLOURS OF SLATE: Natural Gray (Standard), Red, Green, White







KABITENE

SELF-ADHESIVE BITUMINOUS MEMBRANE IN STRIPS

Packaging

PRODUCT	THICKNESS (mm)	WEIGHT (Kg/m²)	ROLL DIMENSIONS (cm)
KABITENE	2	-	5x1500 10X1500 15X1500 20X1500

Rolls packed on wooden pallets, wrapped with polyethylene heat-shrinkable caps.

Warnings

Store vertically, protecting them from atmospheric agents and from too high or too rigid temperatures. Avoid overlapping rolls and pallets.

The contact with solvents and organic fluids can damage the product.

The application surface should be smooth, dry and clean.

The application surface must be previously treated with a suitable bituminous primer, VELQUA, VELABASE or VELAFONDO GRIPERM to eliminate dust and enhance the adhesion of the membrane. The application surface must not have depressions, to avoid stagnation of rain water and must have a sufficient slope to ensure the smooth flow of precipitation (min 1.5%). In the case of applications in vertical development exceeding 2 m or media in strong slope surfaces apply suitable mechanical fasteners in the head of the cloth, then sealed with the junction of the head.

Apply the product at temperature higher than +5°C.

The installation should be discontinued in case of adverse weather conditions (high humidity, rain, etc.).

Review 0. 01.03.201

The above-mentioned values can be subject to update or change. IIVELA S.r.l. reserves the right to modify them at any time without prior notice. For a correct use of our products, see technical specifications. For further information or any special use, please contact our technical department. Any suggestions or technical information provided represent our best knowledge regarding product characteristics and use. Considering different applications and any possible interference of elements beyond our control, the buyer must declare under his own responsibility that the product is suitable for the intended use.